

Material Grade: **1024 (AISI / SAE)**

1. STEELMAKING

	<u>C</u>	<u>Mn</u>	<u>S</u>	<u>P</u>
Min	0.19	1.35		
Max	0.25	1.65	0.05	0.04

2. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of 150M19