

Material Grade: **1040 (AISI / SAE)**

1. STEELMAKING

	<u>C</u>	<u>Mn</u>	<u>S</u>	<u>P</u>
Min	0.37	0.60		
Max	0.44	0.90	0.050	0.040

2. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of 080M40