

Material Grade: **1055 (AISI/SAE)**

1. STEELMAKING

	<u>C</u>	<u>Mn</u>	<u>S</u>	<u>P</u>
Min	0.50	0.60		
Max	0.60	0.90	0.050	0.040

2. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of 070M55