

Material Grade: **1113 (AISI / SAE)**

1. STEELMAKING

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>
Min	0.07		0.80	0.20	
Max	0.15	0.1	1.20	0.30	0.07

2. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of 230M07