

Material Grade: **1213 (AISI/SAE)**

---

**1. STEELMAKING**

	<u>C</u>	<u>Mn</u>	<u>S</u>	<u>P</u>
Min		0.70	0.24	0.07
Max	0.13	1.10	0.33	0.12

**2. TYPICAL MECHANICAL PROPERTIES**

Not specified, although expected to be similar to the ones of 230M07