

Material Grade: **1320 (AISI / SAE)**

---

**1. STEELMAKING**

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>
Min	0.18	0.20	1.60		
Max	0.23	0.35	1.90	0.04	0.04

**2. TYPICAL MECHANICAL PROPERTIES**

Not specified, although expected to be similar to the ones of 150M19