

Title:

1.6747

Material Grade: **1.6747**

Associated Standard: **Werkstoff**

1. STEELMAKING

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>	<u>Cr</u>	<u>Ni</u>	<u>Mo</u>
Min	0.27	0.15	0.40			1.30	3.80	0.40
Max	0.33	0.35	0.60	0.035	0.035	1.50	4.20	0.50

2. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of 835M30