

Material Grade: **21NiCrMo2-2**

1. STEELMAKING

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>	<u>Cr</u>	<u>Ni</u>
Min	0.17		0.65			0.35	0.40
Max	0.23	0.40	0.95	0.035	0.035	0.70	0.70

1. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of 8620