

Material Grade: **3310 (AISI / SAE)**

---

**1. STEELMAKING**

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>	<u>Cr</u>	<u>Ni</u>
Min	0.08	0.20	0.45			1.40	3.25
Max	0.13	0.35	0.60	0.025	0.025	1.75	3.75

**2. TYPICAL MECHANICAL PROPERTIES**

Not specified, although expected to be similar to the ones of grade 655M13