

Material Grade: **4617 (AISI / SAE)**

1. STEELMAKING

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>	<u>Cr</u>	<u>Ni</u>	<u>Mo</u>	<u>Cu</u>
Min	0.15	0.15	0.40				1.65	0.20	
Max	0.21	0.35	0.65	0.040	0.035	0.20	2.00	0.30	0.35

2. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of grade 665M17