

Material Grade: **5115 (AISI/SAE)**

1. STEELMAKING

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>	<u>Cr</u>
Min	0.13	0.15	0.70			0.70
Max	0.18	0.35	0.90	0.040	0.035	0.90

2. TYPICAL MECHANICAL PROPERTIES

Not specified, although expected to be similar to the ones of grade 16MnCr5