

Material Grade: **EN3A**

Associated Standard: **BS970: 1955**

1. STEELMAKING

	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>S</u>	<u>P</u>	<u>Cr*</u>	<u>Ni*</u>	<u>Mo*</u>	<u>V*</u>
Min	0.15	0.05	0.40						
Max	0.25	0.35	0.90	0.06	0.06	0.30	0.40	0.15	0.05

(* denotes residual element)

2. TYPICAL MECHANICAL PROPERTIES

Test type	<u>Tensile and hardness test (at room temperature)</u>					
	Yield (Re)	0.2 % proof	UTS (Rm)	Elong (A)	R of A (Z)	Hardness
Unit	<i>TSI</i>	<i>TSI</i>	<i>TSI</i>	%	%	<i>HB</i>
Normalized	Min		28	25		
	Max					